

# HYDROTHERMAL SYNTHESIS OF YTTRIUM ORTHOVANADATE (YVO<sub>4</sub>) AND ITS APPLICATION IN PHOTO CATALYTIC DEGRADATION OF SEWAGE WATER

J. K. Komal<sup>1,\*</sup>, P. Karimi<sup>2</sup> and K. S. Hui<sup>3</sup>

\* *kompaddy@yahoo.com*

Received: April 2010

Accepted: August 2010

1 Department of Environmental Science, University of Mysore, Manasagangothri, Mysore, INDIA.

2 Department of Geology, University of Mysore, Manasagangothri, Mysore, INDIA.

3 Department of Manufacturing Engineering & Engineering Management, City University of Hong Kong, Kowloon Tong, HONG KONG.

**Abstract:** In this paper, YVO<sub>4</sub> powder was successfully synthesized from Vanadium Pentaoxide (V<sub>2</sub>O<sub>5</sub>), Yttrium Oxide (Y<sub>2</sub>O<sub>3</sub>) and ethyl acetate as a mineralizer by hydrothermal method at a low temperature (T=.230°C, and P=100bars).The as-prepared powders were characterized by X-ray Diffraction (XRD), Fourier Transform Infrared Spectroscopy (FTIR), Scanning Electron Microscopy (SEM), UV-V Spectroscopy and Chemical Oxygen Demand (COD) of the sewage water, respectively. The results show that hydrothermal method can greatly promote the crystallization and growth of YVO<sub>4</sub> phase. XRD pattern clearly indicates the tetragonal structure and crystallinity. An FTIR spectrum of the YVO<sub>4</sub> shows the presence of Y-O and V-O bond, respectively. The presence of these two peaks indicates that yttrium vanadate has been formed. UV-V is absorption spectra suggesting that YVO<sub>4</sub> particles have stronger UV absorption than natural sunlight and subsequent photocatalytic degradation data also confirmed their higher photocatalytic activity.

**Keywords:** XRD, FTIR, SEM, Hydrothermal Growth, Photocatalysis, COD.

## 1. INTRODUCTION

Water is one of the primary natural resources and a necessity for sustaining life on earth. Supplying an adequate amount of potable water to the population worldwide for the sake of growing industrial and domestic needs is a gigantic task. The threats of global [1] warming and climate change which aggravate the problem of water shortage, are of particular concern to India as this country largely depends on glaciers and rainfall for water supply.

Water pollution is the contamination [2] of water bodies such as lakes, rivers, oceans and ground water. Water pollution affects organisms and plants that live in these water bodies and, in almost all cases, it damages not only individual species and population but also natural biological communities. It occurs when pollutants are discharged directly or indirectly into water bodies without adequate treatment to remove harmful contaminants.

Environmental contamination, [3] which is growing around the world and in our daily life, is a serious social problem which cannot be

neglected. Examples of such contaminations can be listed as follows:

1. Water pollution by household waste water discharge and industrial discharge.
2. Respiratory diseases caused by air pollutants such as Sox or Nox.
3. Global warming, climate change, glacier melting etc.

The fact is that using energy to eliminate such environmental contamination increases the emission of CO<sub>2</sub> resulting in more global warming. Therefore, it leads to a dilemma of using energy to achieve the anti-pollution goal. Under such circumstances, it can be concluded that a material is needed which can gently [4] harmonize the contaminated environment in order to restore original conditions using natural energy which is a part of the environment and low cost energy which is supplied to the daily life. One solution to this problem which is presented in this research is photo catalysis. YVO<sub>4</sub>, an important [5] optical material, has many wonderful characteristics and optical properties. The Yttrium Orthovanadate (YVO<sub>4</sub>) as an important metal [6]. Rare earth vanadates

( $MVO_4$ , where  $M=Y, Bi, Fe, In$ , etc) has found some wide and practical applications., such as excellent laser host materials in single crystal form, which make it play [7] an important role in almost any devices involving the artificial production [8] of light and display [9] fields, such as excellent [10] polarizer and laser host material. This system has shown an excellent performance in the production [11] of both hydrogen and oxygen in UV and visible light, however its photo catalytic property is poorly understood.

The band gap of  $YVO_4$  is about 3.5eV, [12] which is wider than that of  $InVO_4$ , though both have a V element in their structure. As heterogeneous  $Y^{3+}$  introduced, the crystal structure is modulated to the tetragonal zircon-type consequently. Therefore the electronic structure is also changed and, the band gap is widened.

Hence in this study, an attempt is made to study the photo catalytic application of pure Yttrium Orthovanadate ( $YVO_4$ ).

## 2. MATERIALS AND METHOD

For preparing  $YVO_4$  particles, appropriate amounts of  $Y_2O_3, V_2O_5$  in 1:1molar ratio were dissolved in ethyl acetate as a mineralizer solution, and the entire mixture was stirred in a magnetic stirrer for 15 minutes till a homogeneous solution was obtained and the solution was completely transferred into the Teflon liner of 25ml capacity provided with

general purpose autoclaves of SS316. The use of Teflon liners helps in overcoming the entry of inclusions from the autoclave material into the crystals. The temperature and pressure were kept constant at T-230°C and P-100 bars, respectively, and the experimental duration was 6 hr. After the experimental run the autoclave was taken out from the hot air oven and was cooled naturally at room temperature. The, synthesized material from the Teflon liner was collected and washed with distilled water for 3 to 4 times; then it was dried for 1hr at 60°C in hot air oven in order to eliminate the moisture content form the obtained material. The obtained materials from the hydrothermal method were characterized using X-ray Diffraction (XRD) analysis, which was performed using a Rigaku miniflex2, copper target, ( $\lambda=1.5405\text{\AA}$ ) and in the scanning range of 10- 800 ( $2\theta$ ), Fourier Transform Infrared Spectroscopy (FTIR 460 plus Jasco) Scanning Electron Microscopy (SEM Hitachi model S-3500N), UV-V spectroscopy (minispectroscop SL171,Elco) and Chemical oxygen demand (COD).

The photocatalytic property of the  $YVO_4$  was tested, at first, 0.1601mg of hydrothermally synthesized  $YVO_4$  powder was dispersed into five beakers, which were filled with 40 ml of sewage waste water separately. Prior to irradiation, the suspension were magnetically stirred in a dark condition for 30 min to establish adsorption/degradation equilibrium. The suspensions were then irradiated under the UV




Fig.1. Shows the XRD pattern of the  $YVO_4$  crystal prepared by hydrothermal method

light and sun light. A 400w high-pressure Hg lamp with a maximum emission at about 360 nm was used as a light source.

### 3. RESULTS AND DISCUSSION

YVO<sub>4</sub> crystal has a zircon type structure and belongs to the tetragonal space group of I4<sub>1</sub>/amd with cell dimensions of. a=7.119Å, c=6.289Å [13]. Fig.1 shows the XRD pattern of YVO<sub>4</sub> crystals prepared by hydrothermal method. All the diffraction peaks could be identified as belonging to the tetragonal zircon-type lattice structure of YVO<sub>4</sub>. (JCPDS: 17-0341).The tetragonal-phase YVO<sub>4</sub> can be easily obtained even at T- 230°C. Three predominant diffraction peaks of 2θ=24.7, 33.26 and 49.48 belongings to the crystalline YVO<sub>4</sub> were observed clearly which indicate the relative high crystallinity. It can be concluded that YVO<sub>4</sub> single phase was

formed successively by the hydrothermal method.

Figs 2.A.B.andC. shows the FTIR spectra of YVO<sub>4</sub> particle before and after photodegradation. The infrared spectra of the YVO<sub>4</sub> were recorded in the range of 4000-400cm<sup>-1</sup>, from the FTIR spectra,, It can be observed that a strong peak at 836 cm<sup>-1</sup>, is apparently associated with the characteristic vibrating modes of the VO<sub>4</sub> group and a weak absorption peak of the Y-O (449.333 cm<sup>-1</sup> ). The presence of these two peaks indicates that yttrium orthovanadate has formed and completed the crystallization of the YVO<sub>4</sub>.The following reaction would have occurred during the synthesis:






Fig. 2. A. FTIR of the YVO4

The broad absorption band at 3095.19 cm<sup>-1</sup> corresponds to the OH groups of H<sub>2</sub>O while absorbing to the surface of the crystals. In addition, the FTIR spectra for hydrothermal product show the two bands at 2358.51 cm<sup>-1</sup> and 1646.91 cm<sup>-1</sup>, which are assigned to OH stretching vibration modes for coordinated water. No structural changes could be found in the Infrared spectra of the YVO<sub>4</sub>, before and after photodegradation of the Sewage waste water, meaning that FTIR spectra of the YVO<sub>4</sub> were not changed even after the photodegradation. This




Fig. 2. B. FTIR of the YVO4 crystal after degradation of sewage waste water by sun light.




Fig. 2. C. FTIR of the YVO<sub>4</sub> crystal after degradation of Sewage waste water by UV light.




Fig. 3 .A




Fig.3.B

Fig. 3. Photo degradation of the Sewage waste water by YVO<sub>4</sub> crystal.

indicated that it performed as a photo catalyst without participation in the chemical reaction. In the present research, it can be conclude that YVO<sub>4</sub> acts as a photo catalyst by accelerating the rate of reaction in presence of sunlight and UV

light without participating in the chemical reaction. In this study, YVO<sub>4</sub> shows more photocatalytic degradation for UV light than natural sunlight.

The morphology and grain size of the YVO<sub>4</sub> particles were characterized with SEM. Fig.3. A and B. shows the SEM images of the YVO<sub>4</sub>.The SEM image shows that the products are composed of large quantities of 1D YVO<sub>4</sub> with typical lengths up to several micrometers. An YVO<sub>4</sub> particle, prepared at T-230°C, consists of homogeneous and tetragonal structures. The SEM images shows that YVO<sub>4</sub> particles which are agglomerated may be because of the hydrophobic nature of the mineralizer which is used as a precursor material for the synthesis.

YVO<sub>4</sub> is a semiconductor which turns to a high energy state by receiving light energy and releases electrons form its illuminated surface and jumped to the conduction band leaving a hole in valence band. The hole in the valence band has a strong oxidation power and takes the electron form the OH<sup>-</sup> (hydroxide ion) in the water at the time OH which takes the electron and, becomes OH radicals of very unstable condition. OH radical takes the electron by the strong oxidation from nearby the organic compound in order to become stable. In this way the organic compound is decomposed by the loss of electron and finally become CO<sub>2</sub> and water and released in to the atmosphere. Fig.4 indicates the photo catalytic process.

COD test is commonly used to measure the amount of organic compound in water; most




Fig. 4. The above figure shows basic Photo catalytic process (fujishima, 1972)

**Table 1.** Initial and final COD of the Photo degraded Sewage water by  $YVO_4$  crystal.

COD of the sewage water before photo degradation.	COD of sewage waste water after photo degradation by UV light.	COD of sewage waste water after photo degradation by sun light.
332.28 mg/L.	51.92 mg/L.	259.6 mg/L.

applications of COD determines the amount of organic pollutants found in the waste water making COD a useful measure of water quality.


In this research, 0.1601 gm of Hydrothermally synthesized  $YVO_4$  powder are taken as a catalyst into the five cleaned beakers containing 40 ml of sewage waste water, then the beakers is irradiated to the sunlight and to the UV light for 6 hrs. After 6 hrs of exposure to the UV light and sunlight, the sewage water sample is immediately analyzed for Chemical Oxygen Demand (COD) and UV spectroscopy. Initial COD of the sewage waste water was 256.9 mg/l. However, after being irradiated to the UV light and sunlight reduction was observed in the COD level to 51.92 mg/l and 332.28 mg/l respectively. Spectroscopic measurement showed an increase in the percentage transmission of light. The initial percentage transmission of sewage waste water was 0% and, after the irradiation by sunlight and UV light, the percentage transmission increased

to 90 to 100%. This means that  $YVO_4$  degraded the organic chemicals in the sewage waste water at orbital level. Fig.5 indicates the UV spectroscopic data of the sewage water and Table.1 shows the initial and final Chemical Oxygen Demand (COD) of sewage water before and after photo degradation by  $YVO_4$ .

For the first time, an attempt was made to find the photo catalytic activity of the Yttrium Orthovanadate ( $YVO_4$ ) in degrading sewage waste water. Therefore, the good crystallization and band gap can be considered as key factors, which enhance the photocatalytic performance of the  $YVO_4$  powder.

#### 4. CONCLUSIONS

Homogeneous particles can be easily prepared by a simple and convenient hydrothermal method. Their synthetic temperature can be lowered to T- 230°C and their pressure to P-100 bars, their tetragonal  $YVO_4$  micro particles with 1 $\mu$ m in diameter can be obtained. Obtained results revealed that  $YVO_4$  acts as a photo catalyst and plays a key role in degrading the organic pollutants in the sewage waste water. The major advantage of this research is that the photo degraded sewage waste water can be reused for the external purposes like cleaning and washing and the photo catalyst can be reused for the further research in photocatalytic activities. The influence of hydrothermal treatment temperature on micro particles  $YVO_4$  was revealed by XRD and FTIR measurements. FTIR spectrometry data are in good agreement with XRD results which clearly indicates the  $VO_4$  vibration. As a necessary condition for developing a photocatalyst with a high performance, it would



**Fig. 5.** Photo degradation of the Sewage waste water by  $YVO_4$  crystal.

be important, that the system be designed in a way to produce short water catalyst. Considering the above mentioned results can be concluded that  $YVO_4$  micro particles are promising alternative materials for photocatalyst and may find potential applications in the related fields.

## REFERENCES

1. Gupta, K. R., water crisis in India, Atlanta publications, (2008), 4181, ISBN: 81-269-0958-2.
2. Lixz, Liuh., photo catalytic oxidation using a new catalyst- $TiO_2$  micro sphere-for water and waste water treatment(2003),.1:37(17):3989-94.
3. Liu, Y., Li, J., Novel  $TiO_2$  nano crystals for waste water purification-trapping energy from sun. Water Practice and technology vol No 4 @ IWA publishing 2006, doi:10.2166/wm.2006072.
4. Shinichi k., keilchimaki., degradation of organic compounds on  $TiO_2$  prepared by hydrothermal method in the presence of  $NH_4F$ . 2009, boi: 10.1007, 64-009-0029-5.
5. Byrappa, K., Ramaningaiiah., Growth and morphology of Nd:YVO4 under hydrothermal conditions. Journal of material science, 2006, 41:1415-1421.
6. OConnor, J., Unusual Crystal-Field energy levels and efficient laser properties of YVO4Nd, Appl.Phys.Lett. 1966, 9,407-9.
7. Haiyan xu, Hao W. Preparation and photo catalytic properties of  $YVO_4$  nano powders. Journal of hazardous materials, 2007, 144:82-85.
8. Guicunli, k., Hydrothermal synthesis and characterization of  $YVO_4$  and  $YVO_4:Er^{3+}$  nanobelts and polyhedral microcrystals. JPhys. Chem, 2008, 112(16): 6228-6231.
9. Byrappa, K., Chandrasekhar, C. K, Growth morphology and mechanism of rare earth vanadate crystals under mild hydrothermal conditions, 2007, 306:94-101.
10. Byrappa, K., Nirmala, B., crystal growth of rare earth vanadate laser hosts and in-situ fabrication of their crystal morphology under mild hydrothermal conditions, 2002, PINSA, 68, A, No.3, pp.193-200.
11. Yiminghe, Y., visible light photo degradation of organics over YVO composite catalyst. Journal of hazardous material, 2009 doi: 10.1016.
12. Haiyan xu, Hao W., Preparation and photo catalytic properties of  $YVO_4$  nano powders. Journal of hazardous materials, (2007), 144:82-85.
13. Baglio, J.A and Gashurov, G, Yttrium orthovanadate and its structure, Acta Cryst, (1968).B24, 292.